



MOBIHEL[®]

Produced in HELIOS Tovarna barv, lakov in umetnih smol Količevo d.o.o.

Količevo 65, 1230 Domžale, Slovenia

T +386 1 722 40 00

F +386 1 722 43 10

E info@helios.si

www.helios.si

TECHNICAL DATA SHEET

MOBIHEL PE putty light weight

Use: The product contains special fillers, which reduce density by approx. 30% in comparison to other PE putties. It has excellent applicative characteristics: it is easier to form and to even out irregularities, it is distinguished for excellent sanding.

The application is possible also at lower temperatures 12-15⁰C, then it is necessary to add approx. 2,5% of hardner (by weight) and the drying time will be prolonged to approx. 30-45 min.









Economical use; (1 weight part of putty has by 30% larger volume if compared to standard PE putty), less waste.

Substrate: - sanded and cleaned steel surface

- degreased galvanized steel
- fine sanded aluminium
- slightly sanded galvanized sheet metal
- thoroughly dried through and sanded sealer
- it should not be applied to acid or alkyd primer

Colour shade: white

FOR PROFESSIONAL USE ONLY!

	<p><i>Pot life</i> 3 – 6 minutes / 20°C</p>
	
	<p>20 – 30 minutes / 20°C</p>
	<p>5 minutes</p>
	<p>P 80 – 150</p>
	<p>FURTHER TREATMENT: All 2K sealers from MOBIHEL programme</p>
	<p>EU limit value VOC for this type of products (category II B (b)), which is ready for application is 250 g/l. VOC of this product, ready for use is 200 g/l.</p>
	<p>12 months</p>

