



TEHNIČNE INFORMACIJE  
TECHNICAL DATA SHEET  
TECHNISCHE INFORMATIONEN  
TEHNIČKE INFORMACIJE  
ТЕХНИЧЕСКАЯ ИНФОРМАЦИЯ



**COLOR** industrija sintetičnih smol, barv in lakov, d. d.  
C. komandanta Staneta 4, 1215 Medvode, Slovenija  
T +386 1 36 29 100, F +386 1 36 29 121  
E info@color.si  
www.color.si


**COLOMIX 2K CLEAR COAT MS 2+1  
STANDARD anti scratch**

**Use:** *Final painting of personal vehicles, bus bodies, trucks and other metal objects*

**Type:** *Two-component acrylic fast drying clear coat*

**Substrate:** *Metallic basecoat*

**ONLY FOR PROFESSIONAL USE !**



**COLOMIX 2K hardener 2+1**  
*2:1 by volume*  
*Pot life min 5h/20 °C*











TEHNIČNE INFORMACIJE  
TECHNICAL DATA SHEET  
TECHNISCHE INFORMATIONEN  
TEHNIČKE INFORMACIJE  
ТЕХНИЧЕСКАЯ ИНФОРМАЦИЯ



**COLOR** industrija sintetičnih smol, barv in lakov, d. d.  
C. komandanta Staneta 4, 1215 Medvode, Slovenija  
T +386 1 36 29 100, F +386 1 36 29 121  
E info@color.si  
www.color.si

	1,3-1,4 mm 2-4 bar 2 x (50-60µm)
	5 min/ 20°C - between coats 10 – 15 min/20°C – before drying in oven
	16h/20 °C 30 min/60 °C (object temp.)
	COLOMIX 2K materials react with humidity. Protect material from humidity and moisture. While coating, the ambient relative humidity should not exceed 80%
	EU limit value VOC for this type of products (category II B (e )) in the form, which is ready for application, is 840 g/l. VOC of this product, prepared for use is 530 g/l.
	48 months